



# Human Model Resin

Photoreactive Resin for Dazz 3D L120/L120Pro Printer

Technical Data Sheet

[www.dazz-3d.com](http://www.dazz-3d.com)

Tel: +86-0755-33372859

Email: [dazz@dazz-3d.com](mailto:dazz@dazz-3d.com)

Dazzle Laser Forming Technology Co.,Ltd

K-2F,Junxiangda Building A, Zhongshanyuan Rd.No.9, Nansan Dist ,Shenzhen, Guangdong, China -818052

LCD human model photosensitive resin LC09 is a solvent-free, medium viscosity, high precision photocurable 3D printing resin. Suitable for laser and LED light source. It can be molded in a few seconds under the irradiation of 385nm and 405nm light source. The photosensitive resin mixture formula is optimized and can effectively suppress the beam penetration and avoid deep curing. The minimum layer thickness of single exposure can be controlled at 0.025. Mm. It could achieve high molding precision; fast curing speed with low odor and low irritancy. With low exposure, the resin can be quickly cured with smooth and delicate appearance. With high strength and elasticity modulus, the printed model is very nice with Khaki color. This resin is very suitable for human model and dolls.

## 1.Applications

It can be used to make models in the fields of architecture, dolls, automobiles, medical, consumer electronics, human model etc. It has been used in functional parts, prototype fields. This resin can be used in Dazz L120/L120PRO 3D printer and the same type of LCD 3D printer.

## 2.Technical Data

### 1)Physical Properties of Liquid Resin

Version	F20
Appearance	Khaki, liquid
Specific gravity(25 °C)	1.10-1.14
Viscosity (25°C , cps,NDJ-8S)	800-900cps
Critical Exposure (mj/ cm <sup>2</sup> )	6
Cured Thickness Rang (mm)	0.02-0.10
Recommend Thickness (mm)	0.025-0.10
Solidify Dp thickness (mm)	0.10

### 2)Properties of Cured Resin

Item	Method	Numerical Value (Secondary Cure)
Shore Hardness	ASTM D 2240	82
Tensile Strength (MPa)	ASTM D 638	40-49
Elongation at break(%)	ASTM D 638	13-26
Young's modulus (MPa)	ASTM D 638	730-850
Glass transition temperature (°C)	ASTM D 648	45

### 3)Advice of Secondary Cure

Printed objects are suggested to be secondary cured to increase the hardness. Cure time for reference as below :

UV Power	Correspond Distance	Intensity (100mW/cm <sup>2</sup> )	Cure Time(min)
2000W High-voltage Mercury Lamp	15-20CM	100	1-2
300WHigh-voltage Mercury Lamp	10CM	6	2-3

125W High-voltage Mercury Lamp	10CM	3	3-4
40W LED Tube	10	<1	4-5

### 3. User Guide

1. Pour the photosensitive resin (shake evenly before use to avoid chromatic aberration) into a clean resin tank. Air bubbles will be generated during the pouring process. Stand the resin for 10 minutes. The printing can be started after the bubbles disappear.

2. Adjust the accuracy and speed of the printer according to the model you want to print. After confirming the printing method, press the software to print.

3. The product is sensitive to sunlight and visible light. When the printer is not in use, the remaining photosensitive resin should be poured out from the resin tank and stored in the dark, but it cannot be poured into the unused resin to avoid pollution.

4. The speed of printing depends on the type of 3D printer and the intensity of the laser/ LED light.

5. If the resin come into contact with skin or eyes, rinse immediately with water or soap.

### 4. Post-Processing Procedure and Note

1 The print model should be cleaned with absolute ethanol and can be cleaned with a low-frequency ultrasonic cleaner. If high-frequency and high-power ultrasonic cleaning is used for the model, it may cause certain damage to the surface of the model;

2. Thoroughly blow the model dry with a hair dryer or the like;

3. It is recommended to remove the support for model with supports first, and then post-cure treatment. If you remove the supports after it's been post-cured , it will easily cause damage to the contact surface of the support point;

4. For some occasions where certain toughness is required, you can choose to cure with UV lamp for 5 minutes. The printed parts should be kept in a cool dry place.

### 5. Safety Precautions

**1)Eye Contact:** Immediately flush with plenty of clean water (under eye lids) for at least 20 minutes. Hold eyelids apart to ensure flushing. Washing within one minute of contact is essential to achieve maximum effectiveness. Seek medical attention immediately.

**2)Skin Contact:**Remove contaminated clothing and rinse contact area thoroughly with soap and water.

**3)Dazz 3D resin is not approved for use with food, drink, or medical application on the human body.**

---

4)For additional information please see the Material Safety Data Sheet.

**6.Packing Specification:** 500g/bottle

**7. Storage**

Store the product in a cool, dry place. The remaining photosensitive resin should not be returned to the original bottle. The bottle cap should be tightened after opening. This product can be stored for 12 months at 18-28 °C, and can not be stored frozen.

