

## Resin Technology Data Sheet

Physical Appearance	Liquid (Yellow/Light Yellow/Dark Green)
Density (25°C)	1.05±1.13g/cm <sup>3</sup>
Viscosity (25°C, cps,NDJ-8S)	100-150cps (25°C, m.Pa.s)
Cubical contraction	5.58%-6.02%
Elongation at break	11%-20%
Glass state temperature	78°C
Tensile Strength	42-62MPa